

**EFFECTS OF IMPACT VELOCITY AND STRESS
CONCENTRATORS IN TITANIUM ON FAILURE
BY ADIABATIC SHEARING**

Third Interim Report
(Feb.18/2001 – June17/2001)

Principal Investigator: J.R.KLEPACZKO

**UNITED STATES ARMY EUROPEAN RESEARCH OFFICE
LONDON, UK**

CONTRACT N°: N68171-00-M-5984
R&D 9022-AN-01

Contractor:

Laboratory of Physics and Mechanics of Materials
ISGMP, UMR – CNRS 7554
METZ UNIVERSITY
F-57045 Metz, France

Approved for public release
Distribution unlimited

20010731 094

REPORT DOCUMENTATION PAGEForm Approved
OMB N° 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Services, Directorate for information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188) Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE June 2001	3. REPORT TYPE AND DATES COVERED Interim, Feb. 18/2001 – June 17/2001	
4. TITLE AND SUBTITLE EFFECTS OF IMPACT VELOCITY AND STRESS CONCENTRATORS IN TITANIUM ALLOYS ON FAILURE BY ADIABATIC SHEARING			5. FUNDING NUMBERS N68171-00-M-5984	
6. AUTHOR(S) J.R. KLEPACZKO			8. PERFORMING ORGANIZATION REPORT NUMBER N/A	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) METZ UNIVERSITY – ISGMP LABORATORY OF PHYSICS AND MECHANICS OF MATERIALS METZ UNIVERSITY ISGMP-LPMM ILE DU SAULCY F-57045 METZ Cedex, FRANCE				
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) USA RDSG-UK, AERONAUTICS AND MECHANICS BRANCH Dr. Sam SAMPATH 223 OLD MARYLEBONE RD. LONDON NW1-5 th , UK			10. SPONSORING / MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION / AVAILABILITY STATEMENT DISTRIBUTION UNLIMITED			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 Words) This Interim Report covers the contract period from Feb. 18/2000 to June 17/2001 (third period of three months). During that period a series of tests on the Modified Double Shear specimens (MDS) of different notch geometry loaded by direct impact has been completed. Impact velocities applied were within the following limits : 10 m/s < V < 90m/s (nominal strain rates $5 \cdot 10^3$ 1/s < T < $4.5 \cdot 10^4$ 1/s). The following geometry of notches were tested : U-geometry and I-geometry. That is increased stress concentrators were applied. The material tested was Ti-6Al-4V, delivered by the ARL-APG-AMSRL. This series of tests was performed to complete testing at high strain rates with different stress concentrators and to compare results with the standard MDS geometry. Analysis of oscillograms obtained with those tests are almost finished. Before testing the experimental setup for the direct impact loading has been improved. The experimental results show a substantial rate effects for all notch geometry. The failure criteria and the energy to failure are the tasks to be studied in the near future.				
14. SUBJECT TERMS ADIABATIC SHEAR BANDS, TITANIUM ALLOY Ti-6Al-4V, STRESS CONCENTRATORS IN IMPACT, DYNAMIC SHEAR FAILURE			15. NUMBER OF PAGES 03	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT	

EXTENDED ABSTRACT

During the third period (three months from Feb.18/01 to June 17/01) of the Contract the program was continued as it was being planned. After the tests were completed with the fast servo-hydraulic universal machine of LPMM on all four geometries of specimen, that is Standard (S-shape), U-shape, V-shape and I-shape, the direct impact technique, [1], has been applied for the last three geometry (U,V and I). Impact velocities were varied within the following limits: $10 \text{ m/s} < V < 90 \text{ m/s}$ (nominal strain rates: $5 \cdot 10^3 \text{ 1/s} < \dot{\Gamma} < 4.5 \cdot 10^4 \text{ 1/s}$). All tests were performed on titanium alloy Ti-6Al-4V, supplied by ARL-Aberdeen, MD. The specimens were machined in LPMM - Metz.

The earlier tests performed on the standard geometry, so-called Modified Double Shear (MDS), was a basis for further numerical calculations of Adiabatic Shear Bands (ASB). Improved constitutive relations had been used in those calculations, and one paper has been submitted in Jan./2001 to International Journal of Impact Engineering [2]. The tests performed recently on U, V and I geometry will be a subject of further analyses to identify failure criteria based on the concept of effective strain or on the strain energy density.

The LPMM-Metz has developed under previous contracts, partially granted by the European Research Office of the US Army, a unique experimental technique which enables impact shear testing of materials within a wide range of strain rates, the impact range covers strain rates from $10\text{E}3 \text{ 1/s}$ to $\sim 10\text{E}5 \text{ 1/s}$, [1]. This technique has been applied to perform experiments with three geometries of specimen, that is "U", "V" and "I", such geometries assure different stress concentrators. The main task is to find the role of stress concentrators in Ti-6Al-4V in triggering of ASB.

References

- [1] J.R.Klepaczko, An Experimental technique for Shear Testing at High and Very High Strain Rates, the Case of a Mild Steel., *Int. J. Impact Engng.*, **15**(1994), 25.
- [2] A.S.Bonnet-Lebouvier and J.R.Klepaczko, Numerical Study of Shear Deformation in Ti-6Al-4V at Medium and High Strain Rates, Critical Impact Velocity in Shear, Submitted to *Int. J. Impact Engng.* (2001).

Research reported in this document has been made possible through the support and sponsorship of the US Government through its European Research Office of the US Army. This Interim Report is intended only for the internal management use of the Contractor and the US Government.